



保定盛泰源金属制品有限公司

Baoding Shengtaiyuan Metal Products Co., Ltd.

Address: Xushui County, Baoding City, Hebei prov. China. Email:sales01@sty.steelfiber.com Mobile phone: 8613730250216

Product Catalogue

Hooked Ends Steel Fiber

Material: Cold Drawn Steel Q195

Spec: STY45/25, 30/30, 40/30, 50/30, 47/35, 65/35,
55/50, 67/50, 67/60 etc.

Tensile Strength: $\geq 1100\text{Mpa}$

Color: Bright, Galvanized, Copper

Application: mainly used for steel fiber reinforced concrete terrace, dam surface, tunnel support, airfield runway, highway, shotcrete,

Amount of admixture: 15-25kg/M³

Packing: 20-25kg/bag

Suggestion: aspect ratio ≤ 70



Glued Fibers for Concrete Reinforcement

Material: Cold Drawn Steel Q195

Spec: STY 65/35, 80/50, 67/60, 80/60 etc.

Tensile Strength: $\geq 1100\text{Mpa}$

Color: Bright

Application: mainly used for steel fiber concrete terrace, dam surface, tunnel support, airfield runway, highway, concrete preformed unit.

Amount of admixture :15-25kg/M³

Packing: 20-25kg/bag



保定盛泰源金属制品有限公司

Baoding Shengtaiyuan Metal Products Co., Ltd.

Address: Xushui County, Baoding City, Hebei prov. China. Email:sales01@sty.steelfiber.com Mobile phone: 8613730250216

Flat End Steel Fibers

Material: Cold Drawn Steel Q195

Spec: STY 42/25, 50/30, 58/35, 36/25, 42/30, 50/35,
38/30, 44/35, 50/40 etc.

Tensile Strength: ≥ 800 or 1100Mpa

Color: Bright, Galvanized, Copper

Application: mainly used for steel fiber reinforced concrete bridge, airfield runway, highway

Amount of admixture :15-25kg/M³

Packing: 20-25kg/bag



Copper Coated Micro Fibers

Material: High Tensile Cold Drawn Steel Wire

Spec: Dia0.18-0.22mm length 12-14mm

Tensile Strength: ≥ 2850 Mpa

Application: mainly used for RPC concrete, concrete bridge, airfield runway, highway

Amount of admixture :15-25kg/M³

Packing: 20-25kg/bag

Wavy Steel Fibers

Material: high quality cold drawn steel wire

Spec: Dia 0.45-1.0mm length 30-60mm

Tensile strength:800-1100MPA

Amount of admixture : 20-25kg/M³

Application: mainly used for steel fiber reinforced concrete terrace, pavement and expansion joint of highway





保定盛泰源金属制品有限公司

Baoding Shengtaiyuan Metal Products Co., Ltd.

Address: Xushui County, Baoding City, Hebei prov. China. Email:sales01@sty.steelfiber.com Mobile phone: 8613730250216



Crimped Steel Fibers

Material: steel ingot

Spec: 38x2x0.5mm(equ-dia0.8mm)

Tensile strength >800Mpa

Application:expansion joints and road of bridge

Amount of admixture: 30-80kg/M³ for
road,50-100kg/M³ for bridge